GUIDE FORMULATION || page 1 of 1



Industrial coating Heat resistant anti-corrosion paint up to 650°C solvent-based, black for industrial installations, chimneys and exhaust pipings

Basis

Suppliers

Silicone resin

				R 21401.0 [1]
Silikophen P 50/X			(1)	55.0
Heucodur-Black 9-100			(2)	8.0
Printex L			(3)	2.0
SILLITIN V 85			(4)	6.0
Heucophos ZPO			(2)	6.0
Ben	tone paste)*			2.0
Xyle	ene			10.0
Butyl acetate			11.0	
Total % by weight			100.0	
)*	Bentone paste			
	Bentone 38	15.0	(5)	
	Tego Dispers 700	7.5	(1)	
	Xylene	75.0		
	Isopropanol	2.5		
(1)	Evonik Tego Chemie			
(2)	Heubach			
(3)	Orion Engineered Carbons			
(4)	HOFFMANN MINERAL			
· · /				

(5) Elementis Specialties

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

DE-86633 Neuburg (Donau)
info@hoffmann-mineral.com

