



AKTISIL VM 56

Field of application: Elastomers

1. Description

AKTISIL VM 56 is an activated SILLITIN Z 86, produced by modifying the surface with a vinyl functional group. The by-products split off during the treatment reaction are largely removed during the production process which firmly attaches the functional group to the filler surface. This helps minimize undesirable side effects, as they are potentially encountered with in-situ mixing (direct addition of additive to the compound).

During the vulcanization the vinyl groups of the AKTISIL VM 56 react in the presence of radicals with the polymer.

Characteristics

		free-flowing powder
Appearance		
Color CIELAB scale:	L*	94.0
	a*	1.0
	b*	10.0
Volatile matter at 105 °C		0.5 %
Density		2.6 g/cm ³
Particle size distribution	D ₅₀	2,4 µm
	D ₉₇	12.0 µm
Oil absorption		45 g/100 g

Packaging

Paper bags	á 25 kg
EVA bags	≤ 20 kg
Big Bags	550 - 900 kg
Bulk	≤ 24 t

Shelf life

3 years if stored properly under dry conditions.



2. Applications

In elastomer applications AKTISIL VM 56 can be used as a functional filler either on its own or in combination with other non-reinforcing or reinforcing fillers. The best effect is achieved in radical cured systems (peroxide, high-energy radiation).

It can be used whenever high tensile strength and high modulus, combined with low tensile and compression set, are as important as excellent processing and extrusion properties.

These properties are an ideal combination, in particular for pressure-less cured extruded products and sponge rubber.

Information on compliance with certain regulations/recommendations and other safety-related aspects: [Product safety information](#)

Field of application

- pressure-less cured extruded products (profiles, hoses)
- cable sheaths and cable insulation
- sponge rubber products
- molded products and seals
- radiator hoses (peroxide cured)
- condenser seals

Methods of processing:

Any process commonly used in the rubber industry.

Elastomers:

Radical cured elastomers such as CM, CSM, EPM, EPDM, EVM, HNBR, pre-crosslinked IIR

Metering:

EPM, EPDM:	50 - 250 phr
EVM:	50 - 250 phr
CM:	50 - 250 phr
HNBR:	30 - 150 phr
pre-crosslinked IIR:	50 - 150 phr

