

GLOXIL light iM16k MAM


Functionalized hollow glass microspheres in peroxide cured FKM

Partial replacement of carbon black for weight and cost reduction



GLOXIL light iM16k MAM

A special process creates the **GLOXIL light iM16k MAM** based on the hollow glass microsphere 3M™ Glass Bubble iM16k.





Status quo

Hollow glass microspheres (HGM): used for weight-reduction and at the same time preserving the physical properties, mainly in thermoplastics

BUT: high raw material costs



For elastomers only useful in high priced polymers



Targets

- Compound density
- Compound costs
- Mechanical properties
- Resistance to various liquid media

Combination of HGM with
carbon black in peroxide cured FKM



Formulation + hollow glass microspheres

in phr	Reference	Replacement with HGM
Viton GAL-200S	100	100
Zinkoxyd aktiv	3	3
TAIC-70	4.3	4.3
Trigonox 101-50D-pd	2	2
Carbon Black N 990	30	12
HGM	-	12

HGM	Functionalization
3M™ Glass Bubbles iM16k	-
GLOXIL light iM16k MAM	methacrylic



Compound preparation and curing

Mixing





Open mill	Ø 150 x 300 mm
Batch weight	approx. 900 g
Mill temperature	50 °C for mixing, 20 °C for removal of the sheet
Mixing time	approx. 15 min.

Curing / Post-cure

Curing, lab press	7 min. / 177 °C / 200 bar
Post-cure	2 h / 230 °C




Survival rate of HGM → reduction of density vs. CB → compound costs





Hardness


DIN ISO 7619-1





Tensile strength


DIN 53 504, S2





Elongation at break


DIN 53 504, S2





Modulus 100 %


DIN 53 504, S2



Compression set 70 h / 230 °C / 25 % def.





DIN ISO 815-1, B







Resistance to hot air

94 h / 230 °C, 30' after removal



GLOXIL light iM16k MAM vs. N 990



lower change of
tensile strength,
otherwise similar
properties



GLOXIL light iM16k MAM vs. iM16k



markedly lower
change of properties

Resistance to dist. water 168 h / 60 °C



**GLOXIL light
iM16k MAM
vs. N 990**

comparably low
change of base
properties



**GLOXIL light
iM16k MAM
vs. iM16k**





markedly lower
change of base
properties

+ lower water
absorption



Resistance to fuel FAM B

70 h / 23 °C



GLOXIL light iM16k MAM vs. N 990



comparable change
of base properties
+ lower fuel
absorption

GLOXIL light iM16k MAM vs. iM16k

lower change of base
properties



Resistance to oil OS206304

168 h / 150 °C



GLOXIL light iM16k MAM vs. N 990

comparable change
of base properties
+ more stable
hardness
+ lower oil absorption




GLOXIL light iM16k MAM vs. iM16k

markedly lower
change of tensile
properties
+ lower oil absorption



Functionalization of 3M™ Glass Bubbles iM16k with methacrylic silane





Partial replacement of carbon black N 990 with GLOXIL light iM16k MAM





We supply materials for good ideas!

HOFFMANN MINERAL GmbH
Muenchener Straße 75
DE-86633 Neuburg (Donau)

Phone: +49 8431 53-0
Internet: www.hoffmann-mineral.com
E-mail: info@hoffmann-mineral.com

Our applications engineering advice and the information contained in this memorandum are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.



Results in tabular form

		N 990	iM16k	GLOXIL light iM16k MAM
Rheology				
Mooney Viscosity, ML 1+4, 120 °C	MU	41	48	49
Mooney Scorch, ML +5, 120 °C	min.	29	40	34
Rotorless Curemeter, M _{min} , 177 °C	Nm	0.04	0.05	0.05
Rotorless Curemeter, V _{max} , 177 °C	Nm/min.	2.2	2.2	2.3
Rotorless Curemeter, t ₉₀ , 177 °C	min.	1.0	1.0	1.0
Mechanical properties (cured 7 min. / 177 °C, post-cured 2 h / 230 °C)				
Hardness	Shore A	69	72	73
Tensile strength	MPa	22	15	18
Elongation at break	%	282	325	235
Modulus 100 %	MPa	4.3	3.6	6.6
Compression set 70 h / 230 °C / 25 %	%	25	31	29
Density (not post-cured)	g/cm ³	1.81	1.60	1.56



Results in tabular form

		N 990	iM16k	GLOXIL light iM16k MAM
Resistance to hot air, 94 h / 230 °C, 30' after removal				
Hardness	Shore A	71	75	77
Tensile strength	MPa	26	19	19
Elongation at break	%	269	187	198
Modulus 100 %	MPa	5.5	9.6	9.5
Δ Hardness	Shore A	+2	+3	+4
Δ Tensile strength	%	+19	+22	+6
Δ Elongation at break	rel.%	-5	-43	-16
Δ Modulus 100 %	%	+28	+165	+44



Results in tabular form

		N 990	iM16k	GLOXIL light iM16k MAM
Resistance to dist. water, 168 h / 60 °C				
Hardness	Shore A	68	63	70
Tensile strength	MPa	21	15	15
Elongation at break	%	336	368	260
Modulus 100 %	MPa	3.7	1.9	5.1
Δ Hardness	Shore A	-1	-9	-3
Δ Tensile strength	%	-2	+1	-16
Δ Elongation at break	rel.%	+19	+13	+10
Δ Modulus 100 %	%	-12	-47	-23
Δ Weight	%	+1.4	+4.1	+2.6
Δ Volume	%	+2.8	+6.4	+3.4



Results in tabular form

		N 990	iM16k	GLOXIL light iM16k MAM
Resistance to fuel FAM B, 70 h / 23 °C				
Hardness	Shore A	61	63	65
Tensile strength	MPa	12	6,7	9,0
Elongation at break	%	206	228	176
Modulus 100 %	MPa	3.9	2.2	5.2
Δ Hardness	Shore A	-8	-9	-8
Δ Tensile strength	%	-44	-56	-49
Δ Elongation at break	rel.%	-27	-30	-25
Δ Modulus 100 %	%	-10	-40	-21
Δ Weight	%	+7.0	+6.2	+6.6
Δ Volume	%	+16	+13	+13



Results in tabular form

		N 990	iM16k	GLOXIL light iM16k MAM
Resistance to oil OS206304, 168 h / 150 °C				
Hardness	Shore A	66	71	72
Tensile strength	MPa	18	11	16
Elongation at break	%	256	272	208
Modulus 100 %	MPa	4.4	3.8	6.7
Δ Hardness	Shore A	-3	-1	-1
Δ Tensile strength	%	-15	-25	-10
Δ Elongation at break	rel.%	-9	-16	-12
Δ Modulus 100 %	%	+2	+4	+2
Δ Weight	%	+0.8	+0.9	+0.8
Δ Volume	%	+1.6	+1.3	+0.7