



## AKTIFIT AM

SILFIT Z 91, amino functionalized

Producer: HOFFMANN MINERAL GmbH  
 Muenchener Strasse 75 • DE-86619 Neuburg (Donau)  
 Phone +49 8431 53-0  
 www.hoffmann-mineral.com

Delivery form: Powder

Storage stability: 2 years

Characteristics	Test method	Based on	Specification
Color value L* a* b*	UGR-PV/PT/69	DIN 5033	≥ 95.7 -0.5 – 0.0 0.0 – 1.3
Residue > 40 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 50 mg/kg
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.4 %

Approved by: Dr. Mikhail Meilikhov, Head of Research & Development  
 For further information or questions you are invited to contact us by [erq-mineral@hoffmann-mineral.com](mailto:erq-mineral@hoffmann-mineral.com).