



AKTISIL AM/89

SiO₂ – Al₂ [(OH)₄Si₂O₅] mixture
Silica Kaolinite
SILLITIN Z 89, amino functionalized

Producer: HOFFMANN MINERAL GmbH
Muenchener Strasse 75 • DE-86619 Neuburg (Donau)
Phone +49 8431 53-0
www.hoffmann-mineral.com

Delivery form: Powder

Storage stability: 2 years

Characteristics	Test method	Based on	Specification
Color value L* b*	UGR-PV/PT/69	DIN 5033	94.0 – 97.0 2.0 – 7.0
Residue > 40 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 100 mg/kg
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.6 %
Water content (Karl Fischer)	UGR-PV/PT/48	DIN 51 777	≤ 0.6 %
Air-jet screening method > 125 µm	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.3 %