



AKTISIL PF 777/89

SiO₂ – Al₂ [(OH)₄Si₂O₅] mixture

Silica Kaolinite

SILLITIN Z 89, alkyl functionalized

Producer: HOFFMANN MINERAL GmbH
 Muenchener Strasse 75 • DE-86619 Neuburg (Donau)
 Phone +49 8431 53-0
 www.hoffmann-mineral.com

Delivery form: Powder

Storage stability: 3 years

Characteristics	Test method	Based on	Specification
Color value L* b*	UGR-PV/PT/69	DIN 5033	94.0 – 97.0 2.0 – 7.0
Residue > 40 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 100 mg/kg
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.6 %
Water absorption (Baumann)	UGR-PV/PT/42		≤ 0.1 ml/g
Air-jet screening method > 125 µm	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.3 %

Approved by: Dr. Mikhail Meilikhov, Head of Research & Development
 For further information or questions you are invited to contact us by erq-mineral@hoffmann-mineral.com.