



## AKTISIL Q

SiO<sub>2</sub> – Al<sub>2</sub> [(OH)<sub>4</sub>Si<sub>2</sub>O<sub>5</sub>] mixture

Silica Kaolinite

SILLITIN V 90\*, methacryl functionalized (\* internal product quality)

Producer: HOFFMANN MINERAL GmbH  
 Muenchener Strasse 75 • DE-86619 Neuburg (Donau)  
 Phone +49 8431 53-0  
 www.hoffmann-mineral.com

Delivery form: Powder

Storage stability: 2 years

Characteristics	Test method	Based on	Specification
Color value L* b*	UGR-PV/PT/69	DIN 5033	93.5 – 96.0 2.0 – 7.0
Residue > 40 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 100 mg/kg
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.4 %
Water content (Karl Fischer)	UGR-PV/PT/48	DIN 51 777	≤ 0.4 %
Water absorption (Baumann)	UGR-PV/PT/42		≤ 1.5 ml/g
Air-jet screening method > 125 µm	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.3 %

Approved by: Dr. Mikhail Meilikhov, Head of Research & Development  
 For further information or questions you are invited to contact us by [erq-mineral@hoffmann-mineral.com](mailto:erq-mineral@hoffmann-mineral.com).