

**MATERIAL SPECIFICATION**

Producer: HOFFMANN MINERAL GmbH  
P.O. Box 14 60 • D-86619 Neuburg (Donau)  
Phone (+49-84 31) 53-0 • Fax (+49-84 31) 53-3 30  
Internet: www.hoffmann-mineral.com  
Email: info@hoffmann-mineral.com

Commercial product name: **AKTIFIT PF 115**  
SILFIT Z 91 coated with amino silane

Delivery form: Powder


Storage stability: 2 years

Characteristics	Test method	Based on	Specification
Color value	UGR-PV/PT/69	DIN 5033	L* = $\geq$ 93 a* = -0,5 – 0 b* = 0 – 1.0
Residue > 40 $\mu$ m	UGR-PV/PT/43	DIN EN ISO 787 part 18	$\leq$ 50 [mg/kg]
Volatile matter at 105 °C RT 20°C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	$\leq$ 0.4 [%]
Water absorption (Baumann)	UGR-PV/PT/42		$\leq$ 0.1 [ml/g]

Contact person:

  
QA / Dirk Schröder

Approved by:

  
Head of R&D, QM / Dr. Christian Seeger