



AKTIFIT Q

SILFIT Z 91, methacryl functionalized

Producer: HOFFMANN MINERAL GmbH
 P. O. Box 14 60 • DE-86619 Neuburg (Donau)
 Phone +49 8431 53-0
 E-mail: info@hoffmann-mineral.com
www.hoffmann-mineral.com

Delivery form: Powder

Storage stability: 2 years

Characteristics	Test method	Based on	Specification
Color value L* a* b*	UGR-PV/PT/69	DIN 5033	≥ 95.0 - 0.5 – 0.0 0.0 – 1.3
Residue > 40 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 50 mg/kg
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.4 %
Water absorption (Baumann)	UGR-PV/PT/42		≤ 0.1 ml/g
Air-jet screening method > 125 µm	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.3 %

Approved by: Dr. Mikhail Meilikhov, Head of Research & Development
 Contact person: Dirk Schröder, Head of Quality Management