

**MATERIAL SPECIFICATION**

Producer: HOFFMANN MINERAL GmbH  
P.O. Box 14 60 • D-86619 Neuburg (Donau)  
Phone (+49-84 31) 53-0 • Fax (+49-84 31) 53-3 30  
Internet: www.hoffmann-mineral.com  
Email: info@hoffmann-mineral.com

Commercial product name: **AKTISIL VM 56 / 89**

Chemical analysis: SiO<sub>2</sub> – Al<sub>2</sub> [(OH)<sub>4</sub>Si<sub>2</sub>O<sub>5</sub>] mixture  
silica kaolinite  
SILLITIN Z 89 coated with Vinyl silane

Delivery form: Powder

Storage stability: 3 years

Characteristics	Test method	Based on	Specification
Brightness Y	UGR-PV/PT/69	DIN 53 163	82.0 – 87.0
Residue > 40 µm > 200 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 100 [mg/kg] ≤ 20 [mg/kg]
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 1.4 [%]
Water content (Karl Fischer)	UGR-PV/PT/48	DIN 51 777	≤ 0.8 [%]
Air-jet screening method	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.3 [%]

Contact person:



QA / Dirk Schröder

Approved by:



Head of R&D, QM / Dr. Christian Seeger