



## SILLITIN Z 89 PURISS

SiO<sub>2</sub> – Al<sub>2</sub> [(OH)<sub>4</sub>Si<sub>2</sub>O<sub>5</sub>] mixture  
Silica Kaolinite

Producer: HOFFMANN MINERAL GmbH  
P. O. Box 14 60 • DE-86619 Neuburg (Donau)  
Phone +49 8431 53-0  
E-mail: [info@hoffmann-mineral.com](mailto:info@hoffmann-mineral.com)  
[www.hoffmann-mineral.com](http://www.hoffmann-mineral.com)

Delivery form: Powder

Storage stability: Unlimited

Characteristics	Test method	Based on	Specification
Color value L* b*	UGR-PV/PT/69	DIN 5033	95.5 – 97.0 2.0 – 6.0
Residue > 40 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 10 mg/kg
Volatile matter at 105 °C RT 20 °C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.8 %
Particle size distribution D <sub>50</sub> D <sub>97</sub>	UGR-PV/PT/72	ISO 13320	2.4 µm 10.5 µm
pH value	UGR-PV/PT/61	DIN EN ISO 787 part 9	7.0 – 9.2
Air-jet screening method > 125 µm	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.1 %
Electrical conductivity	UGR-PV/PT/57	DIN EN ISO 787 part 14	≤ 100 µS/cm

Approved by: Dr. Mikhail Meilikhov, Head of Research & Development  
Contact person: Dirk Schröder, Head of Quality Management