

## MATERIAL SPECIFICATION

Producer: HOFFMANN MINERAL GmbH  
P.O. Box 14 60 • D-86619 Neuburg (Donau)  
Phone (+49-84 31) 53-0 • Fax (+49-84 31) 53-3 30  
Internet: www.hoffmann-mineral.com  
Email: info@hoffmann-mineral.com

Commercial product name: **SILLITIN Z 89 puriss**

Chemical analysis: SiO<sub>2</sub> – Al<sub>2</sub> [(OH)<sub>4</sub>Si<sub>2</sub>O<sub>5</sub>] mixture  
silica kaolinite

Delivery form: Powder

Storage stability: unlimited

Characteristics	Test method	Based on	Specification
Brightness Y	UGR-PV/PT/69	DIN 53 163	83.5 – 88.0
Residue > 40 µm > 200 µm	UGR-PV/PT/43	DIN EN ISO 787 part 18	≤ 10 [mg/kg] ≤ 1 [mg/kg]
pH-value	UGR-PV/PT/61	DIN EN ISO 787 part 9	7.0 – 9.2
Volatile matter at 105 °C RT 20°C / RH 50 %	UGR-PV/PT/41	DIN EN ISO 787 part 2	≤ 0.8 [%]
Electrical conductivity	UGR-PV/PT/57	DIN EN ISO 787 part 14	≤ 100 [µS/cm]
Particle size distribution d <sub>50</sub> d <sub>97</sub>	UGR-PV/PT/72	ISO 13320	≤ 2.4 [µm] ≤ 10.5 [µm]
Air-jet screening method	UGR-PV/PT/84	DIN EN ISO 4610	≤ 0.3 [%]

Contact person:



QA / Dirk Schröder

Approved by:



Head of R&D, QM / Dr. Christian Seeger