

Guide formulation - page 1 of 1

AUTOMOTIVE INDUSTRY**Profile, solid, black****Door seal, low hardness****25 Shore A, EPDM, sulfur cure**

Guide formulation of Exxon		A.4.0.001
Vistalon 3666		175.00
APF N-683		100.00
SILLITIN Z 86		100.00
Grundöl AP/E Core 2500 (ex Flexon 815)		160.00
Zinc oxide		10.00
Stearic acid		2.00
Sulfur		1.00
MBT		1.50
TMTD		0.75
DPTT		0.75
ZDMC		0.75
TDEC		0.75
Calcium oxide 80 %		10.00
Total phr		562.50
Density	g/cm ³	1.15

Monsanto Rheometer, ± 5°, 180°C

ML, minimum	dNm	4
MH, maximum	dNm	20
ts ₂	min	1.5
t _{C90}	min	3.1

Physical properties**Press cure @ 180°C**

Hardness	Shore A	25
Modulus 100 %	MPa	0.6
Modulus 300 %	MPa	1.8
Tensile strength	MPa	7.3
Elongation at break	%	810

Compression set**Press cure 8 min @ 180°C**

22 h @ 70°C, 25 % deflection	ASTM B	%	28
------------------------------	--------	---	----

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-7/0184/01.2011