

**AUTOMOTIVE INDUSTRY****Profile, solid, black****Car body seals, electrically non-conductive****60 Shore A, EPDM, sulfur cure**

Guide formulations of HOFFMANN MINERAL M 568.2	14	16	15	17	18	19
Keltan 8340A )*	100.00	100.00	100.00	100.00	100.00	100.00
Zinkoxyd aktiv	5.00	5.00	5.00	5.00	5.00	5.00
Stearic acid	1.00	1.00	1.00	1.00	1.00	1.00
PEG 3400	2.00	2.00	2.00	2.00	2.00	2.00
Kezadol GR	10.00	10.00	10.00	10.00	10.00	10.00
Corax N 550/30	135.00	60.00	60.00	60.00	60.00	60.00
SILLITIN N 85	---	155.00	---	---	---	---
SILLITIN Z 86	---	---	155.00	---	---	---
SILLIKOLLOID P 87	---	---	---	155.00	---	---
AKTISIL MM	---	---	---	---	155.00	---
AKTISIL PF 216	---	---	---	---	---	155.00
Process Oil P 460 (ex Sunpar 2280)	65.00	65.00	65.00	65.00	65.00	65.00
Rhenogran DPG-80	0.50	0.50	0.50	0.50	0.50	0.50
Rhenogran MBTS-80	1.30	1.30	1.30	1.30	1.30	1.30
Rhenogran ZBEC-70	0.50	0.50	0.50	0.50	0.50	0.50
Rhenogran S-80	2.00	2.00	2.00	2.00	2.00	2.00
Rhenogran CLD-80	2.00	2.00	2.00	2.00	2.00	2.00
Rhenogran TP-50	0.75	0.75	0.75	0.75	0.75	0.75
Rhenogran CBS-80	0.50	0.50	0.50	0.50	0.50	0.50
Vulkalent E/C	1.00	1.00	1.00	1.00	1.00	1.00
Total phr	326.55	406.55	406.55	406.55	406.55	406.55

)\* No longer available. Recommended: Keltan 8550

**Compound preparation****Mixer Farell 3D, tangential, volume 70 l**

Loading	%		72
Rotor speed	rpm		35
Start temperature (wall)	°C		50
Mixing method:			
Polymer	min		0-1
Rest except sulfur and accelerators	min		1-2
Mixing	min		2-4
Sweep	min		4-4.5
Mixing	min		4.5-6
Dump temperature	°C	135	100-120
Dump onto cooled mill (30°C)			
add sulfur and accelerators			

*Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.*

VM-3/1001/02.2021

Guide formulation - page 2 of 3

			M 568.2	14	16	15	17	18	19
<b>Mooney Viscosity</b>									
ML (1+4) 120°C	DIN 53523, T3	MU	70.9	54.9	52.1	54.9	52.9	50.8	
ML (1+4) 100°C	DIN 53523, T3	MU	91.5	75.0	74.2	73.2	70.3	67.9	
<b>Mooney Scorch</b>									
ML (5 MU) 120°C	DIN 53523, T4	min	8.25	12.25	17.42	11.63	13.72	12.92	
<b>Rotorless curemeter, 170°C</b>									
Mmin	DIN 53529, T3	Nm	0.138	0.105	0.106	0.120	0.107	0.099	
Mmax	DIN 53529, T3	Nm	0.723	0.672	0.723	0.751	0.763	0.700	
t <sub>5</sub>	DIN 53529, T3	min	0.61	0.96	1.28	1.02	0.97	0.96	
t <sub>90</sub>	DIN 53529, T3	min	5.30	6.10	7.50	7.60	7.70	7.60	
<b>Rotorless curemeter, 180°C</b>									
Mmin	DIN 53529, T3	Nm	0.130	0.098	0.101	0.114	0.099	0.090	
Mmax	DIN 53529, T3	Nm	0.669	0.647	0.716	0.760	0.789	0.698	
t <sub>5</sub>	DIN 53529, T3	min	0.52	0.73	0.87	0.75	0.71	0.71	
t <sub>90</sub>	DIN 53529, T3	min	2.50	3.38	4.77	5.40	5.50	5.23	
<b>Vacuum extruder, Ø 90 mm 16D</b>									
Screw speed		rpm					15-18		
Extrusion rate		m/min					7,5		
Temperatures	zone 1 (screw)	°C	75				50		
	zone 2	°C	75				40		
	zone 3	°C	80				50		
	zone 4	°C	90				60		
	zone 5 (head)	°C	110				70		
<b>Cure</b>									
UHF (2 x 6 kW)			length 6 m, air temperature 200°C, typical exit temperature 185°C						
Hot air tunnel			length 3 x 9 m, air temperature 270°C						
Cooling			length 2 x 9 m, water temperature 10°C						

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information. VM-3/1001/02.2021

Guide formulation - page 3 of 3

	M 568.2	14	16	15	17	18	19	
<b>Physical properties</b>								
<b>extruded profile, UHF/hot air 270°C, theoretical residence time 3.6 min</b>								
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	1.171	1.367	1.359	1.355	1.362	1.360
Hardness (piled S2)	DIN ISO 7619-1	Shore A	64	58	57	58	60	62
Modulus 50 %	DIN 53504, S2	MPa	1.82	1.43	1.33	1.44	1.57	1.77
Modulus 100 %	DIN 53504, S2	MPa	4.39	2.04	1.98	2.13	2.99	3.42
Modulus 200 %	DIN 53504, S2	MPa	9.72	3.10	3.16	3.39	5.00	5.76
Modulus 300 %	DIN 53504, S2	MPa	13.72	4.35	4.35	4.65	5.87	7.03
Tensile strength	DIN 53504, S2	MPa	13.9	7.4	8,1	8.5	8.6	8.9
Elongation at break	DIN 53504, S2	%	310	510	535	535	480	415
Tear resistance	DIN ISO 34-1, A	N/mm	7.6	8.9	10.5	10.7	11.9	8.4
<b>Compression set VW-PV 3307</b>								
100 h @ 23°C, 50 % defl.	5 s relaxation	%	20.2	21.2	23.2	24.1	21.0	16.7
100 h @ 70°C, 50 % defl.	5 s relaxation	%	42.4	50.6	54.8	56.3	48.1	50.0
22 h @ 70°C, 50 % defl.	5 s relaxation	%	33.0	40.5	42.2	44.3	32.5	34.5
22 h @ 70°C, 50 % defl.	60 min relaxation	%	23.4	32.1	32.5	35.9	25.9	25.3
72 h @ 23°C, 50 % defl.	5 s relaxation	%	18.2	19.8	19.5	23.8	17.5	13.4
72 h @ 23°C, 50 % defl.	60 min relaxation	%	9.1	11.3	12.2	12.5	10.0	8.4
<b>Volume resistivity</b>								
<b>Press cure @ 170°C</b>								
		min	5.8	6.7	8.3	8.4	8.5	8.4
Press cured	DIN IEC 93	Ω cm	3 x 10 <sup>5</sup>	6 x 10 <sup>11</sup>	6 x 10 <sup>12</sup>	1 x 10 <sup>13</sup>	2 x 10 <sup>12</sup>	2 x 10 <sup>13</sup>
Relaxation 2 h @ 70°C	DIN IEC 93	Ω cm	2 x 10 <sup>5</sup>	4 x 10 <sup>12</sup>	4 x 10 <sup>11</sup>	8 x 10 <sup>12</sup>	1 x 10 <sup>12</sup>	2 x 10 <sup>13</sup>
<b>Air aging, 168 h @ 100°C</b>								
<b>extruded profile, UHF/hot air 270°C, theoretical residence time 3.6 min</b>								
Hardness (piled S2)		Shore A	67	65	63	66	66	68
Modulus 50 %		MPa	2.52	1.89	1.79	1.90	2.20	2.74
Modulus 100 %		MPa	6.18	2.66	2.69	2.89	4.16	5.20
Modulus 200 %		MPa	12.58	4.03	4.14	4.50	6.16	7.62
Modulus 300 %		MPa	---	5.61	5.51	5.98	7.55	---
Tensile strength		MPa	14.8	7.2	8.3	8.7	8.9	8.8
Elongation at break		%	255	385	435	425	390	275
Tear resistance	DIN ISO 34-1, A	N/mm	5.4	5.3	8.5	6.4	7.0	3.8
Δ Hardness (piled S2)		Shore A	+3	+7	+6	+8	+6	+6
Δ Modulus 50 %		%	+38.6	+31.9	+34.2	+32.5	+40.3	+54.5
Δ Modulus 100 %		%	+40.8	+30.5	+35.9	+35.8	+39.5	+52.0
Δ Modulus 200 %		%	+29.5	+30.1	+30.9	+33.0	+23.0	+32.3
Δ Modulus 300 %		%	---	+29.0	+26.7	+28.4	+28.5	---
Δ Tensile strength		%	+6.3	-2.7	+2.9	+2.1	+2.4	-0.7
Δ Elongation at break		%, rel.	-16.9	-25.0	-18.6	-20.3	-18.7	-33.8
Δ Tear resistance		%	-28.6	-40.7	-18.8	-40.8	-41.4	-55.0

**More information on this topic is available in this technical report:**

[Comparison of Mineral Fillers in Non-Conductive Car Body Seals](#)

*Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.*

VM-3/1001/02.2021