

Guide formulation - page 1 of 6

AUTOMOTIVE INDUSTRY**Molding, light-colored****Resistant to Diesel and rape-oil methyl ester (RME)**

65 Shore A, HNBR, peroxide cure

Specification VW TL 524.33

Guide formulation of Zeon Europe	RRS 36
Zetpol 1010	100.0
AKTISIL VM 56	70.0
Rhenosin W 759	10.0
Naugard 445	1.5
Rhenogran ZMMBI-50	3.0
Zinkoxyd aktiv	3.0
Stearic acid	2.0
Luperox F40	8.0
Saret SR-517	5.0
Total phr	202.5

Compound preparation**Branbury mixer**

Loading	%	80
Rotor speed	rpm	60
Temperature	°C	40
Mixing method:		
Add polymer and all rest	min	0
Ram lift and sweep	min	3
Discharge	min	4
Indicated discharge temperature	°C	76
Pyro dump temperature	°C	90
Final power consumption	kWh	0.238

Mill mix cycle

Mill temperature	°C	50
Nip	mm	2
Band up, cut and fold	min	0
Strip and cool	min	3

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-8/0101/10.2014

Mooney Viscosity

ML (1+4) 100°C MU 59

Monsanto MDR

		180°C	190°C
Test time	min	12	6
ML, minimum	dNm	0.88	0.85
MH, maximum	dNm	17.14	16.11
MH – ML	dNm	16.26	15.26
ts ₂	min	0.83	0.62
tC ₅₀	min	1.74	1.04
tC ₈₀	min	---	1.62
tC ₉₀	min	4.15	2.05

Physical properties

			VW TL 524.33
Hardness (3 piled sheets)	Shore A	66	65 ± 5
Tensile strength	MPa	19.6	> 10
Modulus 100 %	MPa	3.4	
Modulus 200 %	MPa	6.8	
Modulus 300 %	MPa	9.3	
Modulus 400 %	MPa	12.1	
Modulus 500 %	MPa	18.4	
Elongation at break	%	490	250 to 550

Compression set

72 h @ 125°C	%	30.5	TBA
168 h @/ 125°C	%	36.0	TBA
504 h @ 125°C	%	54.5	TBA
according to VW specification	%	73.5	TBA

Ozone resistance

48 h @ 23°C, 20 % strain, 200 pphm ok no cracks

Cold bend test 22 h @ -30°C

ok no cracks

Low temperature retraction TR 10

-20

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-8/0101/10.2014

Air aging (Geer), 94 h @ 125°C

Hardness (3 piled sheets)	Shore A		71	
Tensile strength	MPa		20.5	> 10
Modulus 100 %	MPa		4.7	
Elongation at break	%		460	> 250
Δ Hardness	Shore A		+5	0 to +8
Δ Tensile strength	%		+4.6	
Δ Modulus 100 %	%		+38.2	
Δ Elongation at break	%, rel.		-6.1	

Immersion in Diesel, 94 h @ 23°C

		after stress	re-dried 22 h @ 80°C	
Hardness (3 piled sheets)	Shore A	65	66	
Tensile strength	MPa	20.9	20.2	> 10
Modulus 100 %	MPa	3.3	3.6	
Elongation at break	%	510	500	> 250
Δ Hardness	Shore A	-1	0	-6 to +2
Δ Tensile strength	%	+6.6	+3.1	
Δ Modulus 100 %	%	-2.9	+5.9	
Δ Elongation at break	%, rel.	+4.1	+2.0	
Δ Volume	%	+2.3	-0.3	
Δ Weight	%	+1.5	---	0 to +5
Δ Weight	%	---	-0.4	-2 to 0

Immersion in RME, 94 h @ 23°C

		after stress	re-dried 22 h @ 80°C	
Hardness (3 piled sheets)	Shore A	62	65	
Tensile strength	MPa	20.4	19.1	> 10
Modulus 100 %	MPa	3.0	3.0	
Elongation at break	%	520	500	> 250
Δ Hardness	Shore A	-4	-1	-6 to +2
Δ Tensile strength	%	+4.1	-2.6	
Δ Modulus 100 %	%	-11.8	-11.8	
Δ Elongation at break	%, rel.	+6.1	+2.0	
Δ Volume	%	+2.5	+1.3	
Δ Weight	%	+1.4	+0.7	0 to +10

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information. VM-8/0101/10.2014

		RRS 36		
		VW TL 524.33		
		after stress	re-dried 22 h @ 80°C	
Immersion in Diesel, 94 h @ 80°C				
Hardness (3 piled sheets)	Shore A	59	65	
Tensile strength	MPa	20.0	18.5	> 10
Modulus 100 %	MPa	3.0	3.9	
Elongation at break	%	510	470	> 250
Δ Hardness	Shore A	-7	-1	-12 to +2
Δ Tensile strength	%	+2.0	-5.6	
Δ Modulus 100 %	%	-11.8	+14.7	
Δ Elongation at break	%, rel.	+4.1	-4.1	
Δ Volume	%	+8.6	+0.04	
Δ Weight	%	+5.1	---	-2 to +8
Δ Weight	%	---	-0.5	-5 to +1
Immersion in RME, 94 h @ 80°C				
		after stress	re-dried 22 h @ 80°C	
Hardness (3 piled sheets)	Shore A	58	60	
Tensile strength	MPa	19.2	18.2	> 10
Modulus 100 %	MPa	3.1	3.0	
Elongation at break	%	480	490	> 250
Δ Hardness	Shore A	-8	-6	-12 to +2
Δ Tensile strength	%	-2.0	-7.1	
Δ Modulus 100 %	%	-8.8	-11.8	
Δ Elongation at break	%, rel.	-2.0	0	
Δ Volume	%	+8.5	+6.1	
Δ Weight	%	+5.1	+3.5	0 to +15

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-8/0101/10.2014

		RRS 36		VW TL 524.33
		after stress	re-dried 22 h @ 80°C	
Immersion in Diesel, 504 h @ 80°C				
Hardness (3 piled sheets)	Shore A	61	66	
Tensile strength	MPa	20.0	17.3	> 7
Modulus 100 %	MPa	3.3	4.3	
Elongation at break	%	500	470	> 150
Δ Hardness	Shore A	-5	0	-17/-15 to +2
Δ Tensile strength	%	+2.0	-11.7	
Δ Modulus 100 %	%	-2.9	+26.5	
Δ Elongation at break	%, rel.	+2.0	-4.1	
Δ Volume	%	+7.6	-0.9	
Δ Weight	%	+4.5	---	-3 to +15
Δ Weight	%	---	-1.2	-10 to +1
Immersion in RME, 504 h @ 80°C				
		after stress	re-dried 22 h @ 80°C	
Hardness (3 piled sheets)	Shore A	60	61	
Tensile strength	MPa	18.8	17.3	> 7
Modulus 100 %	MPa	3.3	3.4	
Elongation at break	%	450	450	> 150
Δ Hardness	Shore A	-6	-5	-17/-15 to +2
Δ Tensile strength	%	-4.1	-11.7	
Δ Modulus 100 %	%	-2.9	0	
Δ Elongation at break	%, rel.	-8.2	-8.2	
Δ Volume	%	+10.2	+7.3	
Δ Weight	%	+6.4	+4.6	0 to +35

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-8/0101/10.2014

Immersion in RME, 168 h @ 100°C

Hardness (3 piled sheets)	Shore A	57
Tensile strength	MPa	19.6
Modulus 100 %	MPa	3.3
Elongation at break	%	460
Δ Hardness	Shore A	-9
Δ Tensile strength	%	0
Δ Modulus 100 %	%	-2.9
Δ Elongation at break	%, rel.	-6.1
Δ Volume	%	+9.8
Δ Weight	%	+5.8

Immersion in RME, 504 h @ 100°C (RME refreshed every 168 h)

Hardness (3 piled sheets)	Shore A	58
Tensile strength	MPa	12.6
Modulus 100 %	MPa	2.4
Elongation at break	%	410
Δ Hardness	Shore A	-8
Δ Tensile strength	%	-35.7
Δ Modulus 100 %	%	-29.4
Δ Elongation at break	%, rel.	-16.3
Δ Volume	%	+7.3
Δ Weight	%	+4.6

Immersion in RME, 1008 h @ 100°C (RME refreshed every 168 h)

Hardness (3 piled sheets)	Shore A	55
Tensile strength	MPa	13.9
Modulus 100 %	MPa	3.7
Elongation at break	%	350
Δ Hardness	Shore A	-11
Δ Tensile strength	%	-29.1
Δ Modulus 100 %	%	+8.8
Δ Elongation at break	%, rel.	-28.6
Δ Volume	%	+29.1
Δ Weight	%	+20.9

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-8/0101/10.2014