

Guide formulation - page 1 of 1

AUTOMOTIVE INDUSTRY**Radiator hose****High heat resistance****65 Shore A, EPDM, peroxide cure**

Guide formulation of DSM (now Arlanxeo)	S 7599
Keltan 8340A)*	70
Keltan 778Z)**	30
Polyethylene glycol	4
Magnesium oxide 80%	4
Corax N 550	30
Durex 0	40
SILLITIN N 85	25
TMQ	1
Paraffin oil	42
DHBP 40%	5
Perkadox 14-40 MB	3
TMPT	2
Total phr	256

)* No longer available. Recommended: Keltan 8550C

)** No longer available. Recommended: Keltan 5470C

excellent set properties (CS 22 h @ 160°C acc. VW after 5 s of release < 35 %) and maximum heat aging resistance (retention of elongation at break at 336 h @ 150°C > 60 %, rel.)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-10/0199/06.2022