

Guide formulation - page 1 of 3

AUTOMOTIVE INDUSTRY**Molding, black****Molded parts for automotive oil seals, replacement of carbon black N-990**

70 Shore A, NBR, sulfur cure

Specification ASTM D2000

	Control N-990	AKTISIL PF 216	AKTIFIT AM	SILFIT Z 91	SILLITIN Z 86	SILLITIN N 82
Guide formulations of HOFFMANN MINERAL M 630.0	1	7	3	2	5	6
Krynac 2950 F)*	100,0	100,0	100,0	100,0	100,0	100,0
Zinkoxyd aktiv	5,0	5,0	5,0	5,0	5,0	5,0
Stearic acid	0,5	0,5	0,5	0,5	0,5	0,5
Agerite Resin D	2,0	2,0	2,0	2,0	2,0	2,0
Corax N 550	60,0	60,0	60,0	60,0	60,0	60,0
Carbon Black N-990	50,0	---	---	---	---	---
AKTISIL PF 216	---	50,0	---	---	---	---
AKTIFIT AM	---	---	50,0	---	---	---
SILFIT Z 91	---	---	---	50,0	---	---
SILLITIN Z 86	---	---	---	---	50,0	---
SILLITIN N 82	---	---	---	---	---	50,0
Mediaplast NB 4	10,0	10,0	10,0	10,0	10,0	10,0
Vulkacit Thiuram/C	2,5	2,5	2,5	2,5	2,5	2,5
Vulkacit CZ/C	2,0	2,0	2,0	2,0	2,0	2,0
Sulfur	0,2	0,2	0,2	0,2	0,2	0,2
Total phr	232,2	232,2	232,2	232,2	232,2	232,2

)* No longer available. Recommended: NBR, 30 % ACN, ML 1+4 (100 °C): 53 MU

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-0/0318/03.2018

Guide formulation - page 2 of 3

			Control N-990	AKTISIL PF 216	AKTIFIT AM	SILFIT Z 91	SILLITIN Z 86	SILLITIN N 82		
M 630.0			1	7	3	2	5	6		
Mooney Viscosity										
ML (1+4) 100°C	DIN 53523, T3	MU	78	78	74	75	80	82		
ML (1+4) 120°C	DIN 53523, T3	MU	58	62	56	57	63	62		
Mooney Scorch										
ML (5 MU) 120°C	DIN 53523, T4	min	15	16	12	14	13	16		
Rotorless curemeter, 170°C										
M _{min}	DIN 53529, T3	Nm	0.09	0.10	0.09	0.10	0.11	0.10		
M _{max}	DIN 53529, T3	Nm	0.70	0.68	0.64	0.63	0.61	0.60		
t ₅	DIN 53529, T3	min	0.61	0.65	0.56	0.60	0.60	0.63		
t ₁₀	DIN 53529, T3	min	0.86	0.90	0.76	0.84	0.84	0.88		
t ₉₀	DIN 53529, T3	min	3.3	2.8	2.7	2.8	2.7	2.7		
V _{max}	DIN 53529, T3	Nm/min	0.39	0.46	0.36	0.36	0.35	0.36		
Time V _{max}	DIN 53529, T3	min	1.87	1.48	1.86	1.89	1.74	1.68		
Mechanical properties										
Press cure 5 min @ 170°C										
Density	DIN EN ISO 1183-1	g/cm ³	1.283	1.340	1.343	1.343	1.342	1.340	ASTM D2000	
Hardness	DIN ISO 7619-1	Shore A	70	67	67	67	67	65	Base values	
Tensile strength	DIN 53504, S2	MPa	15.6	15.1	13.6	14.1	13.9	12.6	70 ± 5	
Modulus 50 %	DIN 53504, S2	MPa	2.2	2.4	2.0	2.0	1.9	1.9	> 10 / > 14	
Modulus 100 %	DIN 53504, S2	MPa	5.0	5.1	3.7	3.7	3.7	3.2		
Modulus 200 %	DIN 53504, S2	MPa	12.2	11.4	7.5	7.4	7.6	6.5		
Modulus 300 %	DIN 53504, S2	MPa	---	14.9	11.7	11.8	12.0	10.7		
Elongation at break	DIN 53504, S2	%	286	309	367	381	377	382	> 250	
Rebound	DIN 53512	%	39	39	39	39	39	39		
Tear resistance	DIN ISO 34-1, A	N/mm	9.2	9.6	11.0	10.7	10.8	12.1		
Compression set 22 h @ 100°C, 25 % deflection	DIN ISO 815, B	%	15.7	19.1	15.9	17.6	22.2	23.4	< 25	
Air aging, 70 h @ 125°C										
Δ Hardness		Shore A	+9	+10	+9	+9	+9	+10	Grade 2 + 3	
Δ Tensile strength		%	+5.8	+7.8	+9.0	-3.3	+1.8	+3.5	0 / +15	
Δ Modulus 50 %		%	+103	+93	+105	+81	+91	+96	max. -25	
Δ Elongation at break		%, rel.	-37	-39	-36	-39	-36	-45	max. -50	

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information. VM-0/0318/03.2018

Guide formulation - page 3 of 3

		Control N-990	AKTISIL PF 216	AKTIFIT AM	SILFIT Z 91	SILLITIN Z 86	SILLITIN N 82	
M 630.0		1	7	3	2	5	6	
Immersion in reference oil IRM 901, 70 h @ 125°C								Grade 2
Δ Hardness	Shore A	+9	+10	+10	+8	+9	+10	0 / +10
Δ Tensile strength	%	+13.1	+4.0	+12.0	+2.1	-1.9	+5.9	max. -20
Δ Elongation at break	%, rel.	-22	-32	-27	-24	-26	-28	max. -35
Δ Weight	%	-5.9	-5.6	-5.9	-5.8	-5.7	-5.6	
Δ Volume	%	-7.0	-7.2	-7.4	-7.1	-7.1	-6.9	-15 / +5
Immersion in reference oil IRM 903, 70 h @ 125°C								Grade 2
Δ Hardness	Shore A	-4	-2	-4	-5	-4	-4	± 10
Δ Tensile strength	%	+6.4	+6.3	+0.7	+2.7	-4.0	+3.8	max. -15
Δ Elongation at break	%, rel.	-11.0	-10.9	-18.9	-14.2	-13.8	-11.6	max. -30
Δ Weight	%	+4.3	+4.8	+4.5	+4.5	+4.8	+4.9	
Δ Volume	%	+6.6	+7.3	+7.3	+7.2	+7.6	+7.3	0 / +25
Immersion in reference fuel Liquid C, 70 h @ 150°C								Grade 2
Δ Hardness	Shore A	-19	-15	-18	-19	-20	-20	0 / -30
Δ Tensile strength	%	-42	-45	-45	-46	-36	-48	max. -60
Δ Elongation at break	%, rel.	-45	-46	-49	-45	-37	-49	max. -60
Δ Weight	%	+27	+27	+26	+26	+27	+26	
Δ Volume	%	+43	+43	+44	+43	+46	+44	0 / +50
Immersion in reference oil IRM 901, 70 h @ 150°C								Grade 3
Δ Hardness	Shore A	+10	+10	+10	+10	+10	+10	0 / +10
Δ Tensile strength	%	+7.4	+8.2	+9.1	+6.0	+0.2	+9.6	max. -20
Δ Elongation at break	%, rel.	-21	-25	-21	-23	-26	-28	max. -40
Δ Weight	%	-5.9	-5.8	-5.9	-5.8	-5.7	-5.6	
Δ Volume	%	-7.2	-7.2	-7.5	-7.2	-7.2	-7.1	-15 / +5
Immersion in reference oil IRM 903, 70 h @ 150°C								Grade 3
Δ Hardness	Shore A	-7	-5	-7	-8	-7	-6	± 10
Δ Tensile strength	%	-0.1	-2.8	+8.4	+4.0	+5.0	+1.2	max. -35
Δ Elongation at break	%, rel.	-6.6	-8.4	-2.4	-4.3	-4.6	-12.3	max. -35
Δ Weight	%	+6.6	+5.7	+6.4	+6.8	+6.8	+6.9	
Δ Volume	%	+9.5	+8.7	+9.7	+10.1	+10.2	+10.3	0 / +25

More information on this topic is available in this technical report:

[Molded NBR Parts for Automotive Oil Seals ASTM D2000 - Replacement of Carbon Black N990](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-0/0318/03.2018