

## MACHINERY and EQUIPMENT Appliance, Gasket, light-colored

### Neuburg Siliceous Earth as an acid resistant and tintable alternative to carbon black 65 Shore A, FKM, peroxide cure

	Control N-990	AKTIFIT VM	AKTIFIT PF 111	AKTIFIT AM	AKTIFIT PF 115	AKTISIL AM	AKTISIL Q
Guide formulations of HOFFMANN MINERAL M 638.0	31	10	11	8	9	5	7
Vitalon GAL-200S	100	100	100	100	100	100	100
Zinkoxyd aktiv	3	3	3	3	3	3	3
Diak No. 7	3	3	3	3	3	3	3
Varox DBPH-50	2	2	2	2	2	2	2
Carbon Black N-990	30	---	---	---	---	---	---
AKTIFIT VM	---	30	---	---	---	---	---
AKTIFIT PF 111	---	---	30	---	---	---	---
AKTIFIT AM	---	---	---	30	---	---	---
AKTIFIT PF 115	---	---	---	---	30	---	---
AKTISIL AM	---	---	---	---	---	30	---
AKTISIL Q	---	---	---	---	---	---	30
Total phr	138	138	138	138	138	138	138

#### Evaluation Neuburg Siliceous Earth vs. carbon black N-990

The rating indicates which type of Neuburg Siliceous Earth improves (+) or equals the corresponding property compared to carbon black. Signs highlighted in green mean that this product within Neuburg Siliceous Earth achieves the best value for this property.

Cure speed	=	=	+	+	+	=
Viscosity	+	+	+	+	+	+
Tensile strength	+	=	=	=	+	=
Elongation at break		=	=	=	=	
Modulus 100 %	+	+	+	+	+	+
Tear resistance		=	=	+	=	=
Compression set ISO, 200°C	=	=	=	=	=	=
Compression set ISO, 200°C, no post cure	=	=	=	=	=	+
Compression set ISO, 232°C	=	=				=
Compression set ISO, 232°C, no post cure	=					+
Compression set VW 23°C	=	=	=		+	=
Compression set VW 150°C	+	+	=	=	+	=
Hot air resistance 210°C	=	=	=		=	+
Hot air resistance 230°C	+	=	=		=	+
Fuel resistance	=	=	=	=	=	=
Oil resistance		+	+		+	+
Resistance to acetic acid	=	=	=	=	=	+

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

VM-1/0318/02.2019

Guide formulation - page 2 of 3

			Control N-990	AKTIFIT VM	AKTIFIT PF 111	AKTIFIT AM	AKTIFIT PF 115	AKTISIL AM	AKTISIL Q
		M 638.0	31	10	11	8	9	5	7
<b>Mooney Viscosity</b>									
ML (1+4) 100°C	DIN 53523, T3	MU	67	63	63	64	66	62	61
<b>Rotorless curemeter, 177°C</b>									
M <sub>min</sub>	DIN 53529, T3	Nm	0.04	0.04	0.04	0.04	0.05	0.04	0.04
V <sub>max</sub>	DIN 53529, T3	Nm/min	3.3	3.4	3.5	4.1	3.8	4.0	3.6
t <sub>90</sub>	DIN 53529, T3	min	0.8	0.8	0.9	0.8	0.8	0.8	0.8
<b>Mechanical properties</b>									
<b>Press cure 7 min @ 177°C</b>									
Hardness	DIN ISO 7619-1	Shore A	65	64	65	65	65	64	63
Modulus 50 %	DIN 53504, S2	MPa	1.58	1.70	1.68	1.68	1.72	1.83	1.60
Modulus 100 %	DIN 53504, S2	MPa	3.2	3.9	3.5	3.7	3.6	4.2	3.6
Tensile strength	DIN 53504, S2	MPa	17	22	16	18	17	19	16
Elongation at break	DIN 53504, S2	%	330	278	336	364	395	312	257
Tear resistance	DIN ISO 34-1, A	N/mm	4.6	3.1	5.4	4.7	6.0	4.5	4.0
Compression set	DIN ISO 815, B								
70 h @ 200°C, 25 % deflection		%	21	20	21	20	21	21	18
70 h @ 232°C, 25 % deflection		%	26	25	28	28	32	30	20
<b>Post cure 2 h @ 232°C</b>									
Hardness	DIN ISO 7619-1	Shore A	66	65	66	66	65	66	65
Modulus 50 %	DIN 53504, S2	MPa	1.66	1.75	1.76	1.83	1.84	1.92	1.72
Modulus 100 %	DIN 53504, S2	MPa	3.6	4.4	4.0	4.6	4.3	4.9	4.3
Tensile strength	DIN 53504, S2	MPa	21	26	23	23	20	24	20
Elongation at break	DIN 53504, S2	%	314	272	351	320	339	311	271
Tear resistance	DIN ISO 34-1, A	N/mm	4.4	3.2	4.9	4.5	6.7	3.9	4.1
Abrasion (10 N)	DIN ISO 4649	mm <sup>3</sup>	53	60	72	67	74	71	73
Compression set	DIN ISO 815, B								
70 h @ 200°C, 25 % deflection		%	20	21	19	20	20	21	20
70 h @ 232°C, 25 % deflection		%	26	26	24	30	32	29	23
Compression set	VW PV 3307								
94 h @ 23°C, 50 % deflection		%	50	53	50	48	54	39	48
94 h @ 150°C, 50 % deflection		%	41	37	36	38	39	34	38
<b>Air aging, DIN 53508, 504 h @ 210°C, post cured specimen, measured 30 min after exposure</b>									
Hardness		Shore A	69	68	68	68	69	69	67
Tensile strength		MPa	24	25	23	25	19	22	24
Elongation at break		%	314	323	320	330	252	304	356
Δ Hardness		Shore A	+3	+2	+2	+1	+3	+2	0
Δ Tensile strength		%	+16	-3	+3	+8	-2	+8	+11
Δ Elongation at break		%, rel.	0	+19	-9	+3	-26	-2	+31

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information. VM-1/0318/02.2019

Guide formulation - page 3 of 3

	Control N-990	AKTIFIT VM	AKTIFIT PF 111	AKTIFIT AM	AKTIFIT PF 115	AKTISIL AM	AKTISIL Q	
M 638.0	31	10	11	8	9	5	7	
<b>Air aging, DIN 53508, 94 h @ 230°C, post cured specimen, measured 30 min after exposure</b>								
Hardness	Shore A	69	67	68	67	68	68	65
Tensile strength	MPa	24	26	27	27	22	28	23
Elongation at break	%	292	283	313	314	247	299	331
Δ Hardness	Shore A	+3	+2	+2	+1	+3	+2	0
Δ Tensile strength	%	+14	+2	+18	+17	+11	+15	+16
Δ Elongation at break	%, rel.	-7	+4	-11	-2	-27	-4	+22
<b>Immersion in FAM B, 70 h @ 23°C, post cured specimen</b>								
Hardness	Shore A	59	58	59	58	58	58	58
Tensile strength	MPa	12	14	11	12	10	11	10
Elongation at break	%	231	220	255	246	268	238	206
Δ Hardness	Shore A	-7	-7	-7	-8	-7	-8	-7
Δ Tensile strength	%	-44	-46	-51	-48	-50	-53	-49
Δ Elongation at break	%, rel.	-26	-19	-27	-23	-21	-24	-24
Δ Weight	%	+6.7	+7.3	+7.8	+8.0	+8.0	+6.8	+8.0
Δ Volume	%	+15	+18	+19	+19	+19	+17	+19
<b>Immersion in OS 206 304, 168 h @ 150°C, post cured specimen</b>								
Hardness	Shore A	65	65	65	65	66	65	64
Tensile strength	MPa	17	19	21	22	16	22	21
Elongation at break	%	266	210	295	291	231	281	291
Δ Hardness	Shore A	-1	0	-1	-1	+1	-1	-1
Δ Tensile strength	%	-19	-26	-7	-3	-20	-9	+2
Δ Elongation at break	%, rel.	-15	-23	-16	-9	-32	-10	+7
Δ Weight	%	+0.8	+0.8	+0.7	+0.6	+0.6	+0.7	+0.6
Δ Volume	%	+1.4	+1.4	+1.2	+0.9	+1.4	+1.2	+0.7
<b>Immersion in acetic acid pH3, 168 h @ 100°C, post cured specimen</b>								
Hardness	Shore A	54	52	51	51	52	47	51
Tensile strength	MPa	19	21	15	17	16	19	20
Elongation at break	%	268	265	355	316	304	300	274
Δ Hardness	Shore A	-12	-13	-15	-15	-13	-19	-14
Δ Tensile strength	%	-10	-20	-35	-24	-18	-22	-3
Δ Elongation at break	%, rel.	-15	-3	+1	-1	-10	-4	+1
Δ Weight	%	+17	+20	+17	+26	+19	+24	+23
Δ Volume	%	+30	+37	+34	+50	+37	+47	+43

**More information on this topic is available in this technical report:**

[Neuburg Siliceous Earth in Peroxide Cured FKM as an Acid Resistant and Tintable Alternative to Carbon Black N990](#)

*Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.*

VM-1/0318/02.2019