GUIDE FORMULATION || page 1 of 1



AUTOMOTIVE INDUSTRY Grinding polish

			RR 011
Water, softened)	
Thickener		}	30.0
Preservative)	
Emulsifier			5.0
Paraffin oil			5.0
Exxsol D 80	(1)		20.0
SILLITIN V 85	(2)		40.0
Total % by weight			100.0

Mixing start with water and stir in emulsifier

add Exxsol D 80 and paraffin oil while stirring

stir in SILLITIN V 85

finally stir in preservative and thickener

Suppliers (1) ExxonMobil

> HOFFMANN MINERAL (2)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

