## GUIDE FORMULATION || page 1 of 1



## INDUSTRIAL AND HOUSEHOLD CLEANER Eloxal cleaner

		RR 016
Exxsol D 145/160	(1)	35.0
Marlowet 5001	(2)	8.0
Water, softened		26.8
SILLITIN N 85 PURISS	(3)	10.0
Aluminum oxide P 10 feinst	(4)	20.0
Preservative		(as needed) 0.2
Total % by weight		100.0

Mixing start with Exxsol D 145/160 and Marlowet 5001

add water

stir in SILLITIN N 85 PURISS

stir in Aluminum oxide P 10 feinst with a high speed mixer

add preservative

**Suppliers** ExxonMobil (1)

> (2) Sasol

HOFFMANN MINERAL (3)

(4) Almatis

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

