



AUTOMOTIVE INDUSTRY

Car polish, solvent-free, sprayable for hand polishing of micro scratches

Basis: Byk CAR 4056		RR 024
Water		60.0
Preservative		(as needed) 0.2
Optigel WX	(1)	1.0
Disperbyk 2015	(1)	1.5
SILLITIN Z 89	(2)	6.0
Aquacer 565	(1)	7.5
Water		18.4
Byk-9890	(1)	5.4
Total % by weight		100.0

- Mixing**
- premix water, preservative and Optigel WX for 15 min at 1000 rpm
 - add Disperbyk 2015 and SILLITIN Z 89 under stirring
 - stir 15 min at 2000-3000 rpm
 - add Aquacer 565 and water at 2000-3000 rpm over 5 min
 - continue stirring for 15 min at 2000-3000 rpm
 - add Byk-9890 at 500 rpm over 3 min
 - continue stirring at 500 rpm for 15 min

Note Spray a thin layer of the formulation on the painted surface and gently apply by hand using a microfiber towel.

- Suppliers**
- (1) Byk Chemie
 - (2) HOFFMANN MINERAL

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.