**Industrial coating****Anti-corrosion primer, water-based, red**

good wet adhesion, for economic use

Basis Styrene acrylate dispersion

L 00014.2 [3]

Pigment preparation			
	-- part 1 --		
	Demineralized water		15.00
	Edaplan 490	(1)	0.80
	Byk-024	(2)	0.10
	Butyl glycol		3.00
	-- part 2 --		
	Bayferrox 130 M	(3)	8.90
	AKTIFIT PF 115	(4)	13.50
	Heucophos ZPO	(5)	7.00
	Heucorin RZ	(5)	1.00
Let down	-- part 3 --		
	Alberdingk SC 48	(6)	39.70
	Demineralized water		2.90
	-- part 4 --		
	Optifilm Enhancer 300	(7)	1.00
	Byk-024	(2)	0.40
	Byk-349	(2)	0.10
	Ascotran-H10	(8)	0.50
	Ammonia 25 %		0.80
	Resydrol AX 237 W/70 BG	(9)	4.00
	Borch OXY-Coat 1101	(10)	0.10
	Tafigel PUR 41	(1)	1.20
	Total % by weight		100.00

Recommendation**AKTIFIT PF 115**

- stable viscosity level
- improved wet adhesion
- resistance to blistering and corrosion in non-scribed surface area
- strongly inhibited corrosion progress at scribe

**Mixing**

Pigment preparation

- mix raw materials from part 1
- premix raw materials from part 2 and add to part 1
- disperse with high shear for 10 min under cooling

Let down

- charge Alberdingk SC 48 and dilute with water
- add pigment preparation while stirring
- complete step by step with raw materials of part 4

Application


- substrate: cold-rolled steel
- dual-layer coating, dry film thickness (DFT) 150 µm in total
- single-layer coating, DFT 80 µm
- drying 28 d

Technical Data

Solids content (w/w)	56 %
PVC	31 %

Suppliers

- (1) Münzing Chemie
- (2) Byk Chemie
- (3) Lanxess
- (4) HOFFMANN MINERAL
- (5) Heubach
- (6) Alberdingk Boley
- (7) Eastman Chemical Company
- (8) Ascotec
- (9) Allnex
- (10) Borchers



Control with
calcium carbonate
and talc

AKTIFIT PF 115
L 00014.2 [3]

Properties


Dynamic viscosity @ 23 °C			
10 s ⁻¹ , 1 d	Pa·s	1.13	0.74
10 s ⁻¹ , 28 d	Pa·s	1.59	0.75
1000 s ⁻¹ , 1 d	Pa·s	0.30	0.24
1000 s ⁻¹ , 28 d	Pa·s	0.40	0.25
Cross-cut test 2 mm, after tape tear-off		0	0

Humidity test DIN EN ISO 6270-2 CH

Rating according to DIN EN ISO 4628 part 2-5

Dual-layer coating, DFT 150 µm


Cross-cut test 2 mm after 1 h regeneration time and tape tear-off		3	0
Degree of rusting / cracking / flaking	480 h	0	0
Degree of blistering	480 h	4-5 (S3)	0 (S0)



Under-film corrosion

stripped





Control with
calcium carbonate
and talc

AKTIFIT PF 115
L 00014.2 [3]

Salt spray test DIN EN ISO 9227 NSS

Rating according to DIN EN ISO 4628 part 2-5 and 8

Dual-layer coating, DFT 150 µm

Cross-cut test 2 mm

2mm, 1 h regeneration time, tape tear-off

Degree of rusting / cracking / flaking

Degree of blistering

Degree of delamination around a scribe

Degree of blistering / corrosion around a scribe

480 h	480 h	480 h	480 h
4-5	0	4 (S4)	0 (S0)
0	0	0	0
0	0	0	0
240 h	480 h		



stripped



Single-layer coating, DFT 80 µm

120 h

120 h



More information on this topic:

[Neuburg Siliceous Earth in Water-based Corrosion Protection - Acrylate Primer Red](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.