



MACHINERY and EQUIPMENT

Appliance, Gasket, light-colored

Washing machine gasket for dry cleaning machine

Good resistance to perchloroethylene

60 Shore A, NBR, sulfur cure

Guide formulation of Azienda Chimica Milanese Archive	RRS 52
Europrene N 3360	100
Zinkoxid	5
Flectol H)*	2
Stearic acid	1.5
Ultrasil VN 3	20
AKTISIL PF 216	80
TMTM	1.5
CBS	1.5
TMTD	1.5
Hansa Dis T4	7
Sulfur	0.3
Total phr	220.3

)* No longer available. Recommended: Vulkanox HS/LG

Mechanical properties

Density	g/cm ³	1.47
Tensile strength	MPa	11.0
Elongation at break	%	500
Hardness	Shore A	60
Volume change in perchloroethylene, 48 h @ 70 °C	%	2.5

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.