



## Industrial coating

### Road marking paint, white

**Basis** Styrene acrylate

			S 21401.0 [1]
<b>Component A</b>	Styrene acrylate 60 % ATX	(1)	24.0
	Efka FA 4601	(2)	0.2
	Sojalecithin	(3)	0.9
	Isobutyl acetate		6.5
<b>Component B</b>	Aerosil 200	(4)	0.2
	Titanium dioxide		11.0
	Farsil 44	(5)	10.0
	Calcite	(6)	25.0
<b>Component C</b>	SILLITIN Z 89	(7)	9.0
	Toluene		7.0
	Acetone		6.2
	Total % by weight		

**Mixing**

- charge component A
- add and disperse component B
- complete by component C
- adjust viscosity to 35-38 s (6 mm flow cup) by acetone

**Suppliers**

- (1) e. g. Synthalat A 526 HS, Synthopol Chemie
- (2) BASF
- (3) Overlack
- (4) Evonik Industries
- (5) Silmer
- (6) z. B. Durcal 5, Omya
- (7) HOFFMANN MINERAL

#### **More information on this topic:**

[Filler Optimization for Road Marking Paints](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.