



**Industrial coating**  
**UV-curing transparent surfacer for wood**  
**without reactive diluent**

**Basis** Polyester acrylate

Basis: Guide Formulation 4054/11 (March 1994) of BASF		I 45404.0 [1]
Laromer PE 56 F	(1)	63.0
AKTISIL MAM	(2)	35.0
Aerosil 380	(3)	1.0
Soja-Lecithin STA conc.	(4)	0.5
Omnirad 1173	(5)	2.5
Total parts by weight		102.0

**Technical Data**

Consistency		paste
Reactivity	40-60 g/m <sup>2</sup>	approx. 10-20 m/min 1 lamp 120 W/cm

**Suppliers**

- (1) BASF
- (2) HOFFMANN MINERAL
- (3) Evonik Industries
- (4) Lubrizol Coating Additives
- (5) IGM Resins

**More information on this topic:**

[Neuburg Siliceous Earth in UV-Curing Wood Coatings \(Transparent Primer\)](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.