



## Painting material

### Rust inhibitive primer, water-based

**Basis** Vinyl acrylate

		R 10103.2 [2]
<b>Component A</b>	Demineralized water	23.3
	Korrosionsinhibitor L1 (1)	0.2
	Additol XW 330 (2)	0.1
	Byk-035 (3)	0.2
	Dowfax 2A1 (4)	0.5
	Butyl glycol	2.0
<b>Component B</b>	Talkum AT extra )*(5)	10.0
	Bayferrox 130 BM (6)	2.7
	SILLITIN Z 86 (7)	10.0
	Zinkphosphat PZ 20 (8)	5.5
<b>Component C</b>	Haloflex 202 (9)	45.5
	Total % by weight	100.0

)\* Talkum AT extra is no longer available  
Recommended: Finntalc M05N (10)

**Mixing**

- charge component A
- add and disperse component B
- complete by component C

**Technical Data** Viscosity (20°C, DIN 4 mm flow cup) 16 s

**Suppliers**

- (1) C. H. Erbslöh
- (2) Allnex
- (3) Byk Chemie
- (4) Dow Chemical Company
- (5) Omya
- (6) Lanxess
- (7) HOFFMANN MINERAL
- (8) Société Nouvelle des Couleurs Zinciques (SNCZ)
- (9) DSM NeoResins
- (10) Elementis

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.