## GUIDE FORMULATION || page 1 of 1



## Industrial coating

## Heat resistant anti-corrosion paint up to 400°C solvent-based, black for industrial installations, chimneys and exhaust pipings

**Basis** Silicone resin

		R 21402.0 [1]
Silikophen P 80/X	(1)	23.8
Degalan PM 381	(2)	6.8
Printex L	(3)	3.2
Heucodur-Black 9-100	(4)	8.4
SILLITIN V 85	(5)	8.2
n-Butanol		2.1
Xylene		47.5
Total % by weight		100.0

## **Suppliers**

- (1) Evonik Tego Chemie
- (2) **Evonik Industries**
- (3)Orion Engineered Carbons
- (4) Heubach
- HOFFMANN MINERAL (5)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

