

Guide Formulation - page 1 of 1

**Industrial coating  
Anti-corrosion primer for high requirements  
high solid**

Basis: Epoxy resin (bisphenol A/F and polyamido amine adduct)

	Guide Formulation of Heubach		407-04
<b>Component A</b>	Araldite GZ 7071 X 75	(1)	18.40
	Araldite GY 783	(1)	13.80
	n-Butanol		5.00
	Byk-057	(2)	0.45
	Heucophos ZPO	(3)	8.70
	Bayferrox 130 M	(4)	5.30
	SILLITIN Z 86	(5)	31.90
	<i>grind by bead mill</i>		
<b>Component B</b>	Shellsol A 100	(6)	5.00
	Aradur 450	(1)	11.45
	Total parts by weight		100.00
<b>Technical Data</b>	PVC		30.6 %
	PVC / CPVC		0.6
	Solids content		85.0 %
	Anti-corrosion pigment reg. pigment / filler		15.0 Vol-%
<b>Suppliers</b>	(1)	Huntsman Advanced Materials	
	(2)	Byk Chemie	
	(3)	Heubach	
	(4)	Lanxess	
	(5)	HOFFMANN MINERAL	
	(6)	Shell Chemicals	

*Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.*

VM-0/0111/01.2011