

## MACHINERY and EQUIPMENT

### Appliance, Gasket, light-colored

#### Washing machine gasket

45 Shore A, EPDM, sulfur cure

Guide formulation of Exxon		RRS 19
Vistalon 3666		175.0
SILLITIN P 87		100.0
Perkasil KS 300		40.0
Grundöl AP/E Core 600 (ex Flexon 876)		45.0
Zinc oxide		5.0
Stearic acid		2.0
Titanium dioxide		10.0
Diethylene glycol		3.0
Kagevest 25 (ex Polyvest 25)		2.0
Sulfur		1.0
MBT		1.5
Deovulc EG 28		4.5
Total phr		389.0
Density	g/cm <sup>3</sup>	1.20


#### ODR, 180°C

ML, Minimum	dNm	11
MH, Maximum	dNm	35
ts <sub>2</sub>	min	1.3
tC <sub>90</sub>	min	3.6

#### Physical properties

##### Press Cure 5 min @ 180°C

Hardness	Shore A	47
Modulus 100 %	MPa	1.2
Modulus 300 %	MPa	3.4
Tensile strength	MPa	11.0
Elongation at break	%	700
Tear resistance	N/mm	8.7



RRS 19

**Compression set**

24 h @ 100°C	%	35
--------------	---	----

**Tension set**

24 h @ 100°C, 50 %	%	25
--------------------	---	----

**Air aging, 72 h @ 70°C**

Δ Hardness	Shore A	+5
Δ Tensile strength	%	-7
Δ Elongation at break	%, rel.	-6

**Immersion in detergent solution, 72 h @ 95°C**

Δ Hardness	Shore A	0
Δ Volume	%	+1

**Immersion in ASTM Oil 2, 72 h @ 80°C**

Δ Hardness	Shore A	-16
Δ Volume	%	+68

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.