



MACHINERY and EQUIPMENT

Appliance, Gasket, light-colored

Washing machine gasket

40 Shore A, EPDM, sulfur cure

Guide formulations of HOFFMANN MINERAL	M 612.0	with silica		without silica	
		21	16	14	9
Vistalon 3666		175.00	175.00	175.00	175.00
Stearic acid		1.00	1.00	1.00	1.00
Zinkoxyd aktiv		5.00	5.00	5.00	5.00
Aflux S)*		3.00	3.00	3.00	3.00
Diethylene glycol		3.00	3.00	3.00	3.00
Silanogran PV		4.80	4.80	4.80	4.80
SILLITIN P 87		100.00	---	150.00	---
SILFIT Z 91		---	100.00	---	150.00
Perkasil KS 300-pd		25.00	25.00	---	---
Kronos 2222		9.00	9.00	9.00	9.00
Corax N 550/30		0.35	0.35	0.35	0.35
Process Oil P 460 (ex Sunpar 2280)		25.00	25.00	25.00	25.00
Rhenogran MBT-80		2.40	2.40	2.40	2.40
Sulfur		0.70	0.70	0.70	0.70
Rhenogran CLD-80		1.20	1.20	1.20	1.20
Rhenocure TP/S		3.60	3.60	3.60	3.60
Total phr		359.05	359.05	384.05	384.05
Density	g/cm ³	1.19	1.19	1.24	1.24


)* No longer available. Recommended: Aflux 37

The replacement of precipitated silica can be realized without negatively affecting the mechanical properties.


The basic properties of the compounds with SILFIT Z 91 and SILLITIN P 87 are comparable (slightly increased tensile moduli with SILFIT Z 91).

The very bright and neutral color of SILFIT Z 91 enables lower titanium dioxide and carbon black loading.

A further benefit of SILFIT Z 91 is the reduction or total elimination of filler induced mold fouling during the injection.



			with silica		without silica	
M 612.0			21	16	14	9
Mooney Viscosity						
ML (1+4) 120°C	DIN 53523, T3	MU	42	44	38	41
Mooney Scorch						
ML (5 MU) 120°C	DIN 53523, T4	min	7.6	7.4	7.8	7.2
Rotorless curemeter, 180°C						
Mmin	DIN 53529, T3	Nm	0.060	0.058	0.056	0.053
Mmax	DIN 53529, T3	Nm	0.276	0.264	0.276	0.259
t ₅	DIN 53529, T3	min	0.48	0.50	0.44	0.45
t ₉₀	DIN 53529, T3	min	2.33	2.16	2.42	1.98
Physical properties						
Press cure 5 min @ 180°C						
Hardness (piled S2)	DIN ISO 7619-1	Shore A	39	39	42	40
Modulus 50 %	DIN 53504, S2	MPa	0.61	0.59	0.67	0.63
Modulus 100 %	DIN 53504, S2	MPa	0.9	0.9	1.1	1.0
Modulus 200 %	DIN 53504, S2	MPa	1.6	1.6	2.0	2.1
Modulus 300 %	DIN 53504, S2	MPa	2.3	2.5	2.8	3.3
Modulus 500 %	DIN 53504, S2	MPa	3.8	4.3	4.6	5.8
Tensile strength	DIN 53504, S2	MPa	13.9	13.5	14.1	12.1
Elongation at break	DIN 53504, S2	%	860	855	855	810
Rebound	DIN 53512	%	58	61	57	60
Tear resistance	DIN ISO 34-1, A	N/mm	8.5	9.7	9.6	9.4
Compression set	DIN ISO 815, B					
24 h @ 70°C, 25 % deflection		%	16.3	16.2	16.6	15.6
24 h @ 100°C, 25 % deflection		%	36.0	34.6	35.2	34.4
Color						
L*	ISO 7724		54.8	55.4	54.5	54.8
a*	ISO 7724		-1.7	-1.5	-1.7	-1.6
b*	ISO 7724		-0.6	-3.2	-1.4	-3.2



		with silica		without silica	
M 612.0		21	16	14	9
Air aging, 72 h @ 120°C, DIN 53508					
Hardness (piled S2)	Shore A	49	48	49	47
Δ Hardness	Shore A	+10	+9	+7	+7
Air aging, 168 h @ 120°C, DIN 53508					
Hardness (piled S2)	Shore A	50	48	51	50
Modulus 50 %	MPa	1.0	0.9	1.0	0.9
Modulus 100 %	MPa	1.7	1.6	1.9	1.9
Modulus 200 %	MPa	3.4	3.6	4.0	4.6
Modulus 300 %	MPa	4.9	5.4	5.5	6.8
Modulus 500 %	MPa	8.6	8.7	8.8	---
Tensile strength	MPa	10.1	9.3	9.3	8.5
Elongation at break	%	570	520	535	390
Rebound	%	53	62	60	61
Tear resistance		5.2	4.2	4.7	3.2
Δ Hardness	Shore A	+11	+9	+9	+10
Δ Modulus 50 %	%	+57	+49	+55	+49
Δ Modulus 100 %	%	+86	+82	+79	+86
Δ Modulus 200 %	%	+112	+120	+103	+121
Δ Modulus 300 %	%	+113	+115	+95	+105
Δ Modulus 500 %	%	+130	+100	+89	---
Δ Tensile strength	%	-28	-31	-34	-30
Δ Elongation at break	%, rel.	-34	-39	-37	-52
Δ Rebound	%, rel.	+7	+2	+5	+2
Δ Tear resistance	%	-39	-57	-51	-67

More information on this topic

[Silfit Z 91 in Grey-colored Washing Machine Gaskets](#)

Our applications engineering advice and the information contained in this formulation are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.